

and Archaeology, Sining 810007, China

1. Hou, G. *Adv. Food Nutr. Res.* **43**, 143–193 (2001).
2. Institute of Archaeology, Chinese Academy of Social Sciences & Qinghai Provincial Institute of Cultural Relics and Archaeology *Archaeology* **12**, 12–25 (2002).
3. Yang, X. Y., Xia, Z. K. & Yi, M. L. *Chinese Sci. Bull.* **48**, 1877–1881 (2003).
4. Institute of Archaeology *Archaeology* **12**, 58–76 (2003).
5. Ball, T. B., Gardner, J. S. & Anderson, N. Am. J. Bot. **86**, 1615–1623 (1999).
6. Pearsall, D. M. *Paleoethnobotany: A Handbook of Procedures* 2nd edn (Academic, San Diego, 2000).
7. Lu, H. Y. & Liu, K. B. *Div. Distrib.* **9**, 73–87 (2003).

8. Piperno, D. R., Weiss, E., Holst, I. & Nadel, D. *Nature* **430**, 670–673 (2004).
9. Fujita, S., Sugimoto, Y., Yamashita, Y. & Fuwa, H. *Food Chem.* **55**, 209–213 (1996).
10. Shelach, G. J. *World Prehist.* **14**, 363–413 (2000).
11. Institute of Archaeology, Chinese Academy of Social Sciences & Qinghai Provincial Institute of Cultural Relics and Archaeology *Cult. Relics* **2**, 85–91 (2004).
12. Ren, S. N. *Archaeology* **1**, 37–49 (1995).

Supplementary information accompanies this communication on *Nature's* website.

Competing financial interests: declared none.

doi:10.1038/437967a

MICROWAVE DEVICES

Carbon nanotubes as cold cathodes

To communicate, spacecraft and satellites rely on microwave devices, which at present are based on relatively inefficient thermionic electron sources that require heating and cannot be switched on instantaneously. Here we describe a microwave diode that uses a cold-cathode electron source consisting of carbon nanotubes¹ and that operates at high frequency and at high current densities.

Because it weighs little, responds instantaneously and has no need of heating, this miniaturized electron source should prove valuable for microwave devices used in telecommunications.

We constructed a microwave diode in which the carbon-nanotube field-emission source was directly driven at gigahertz (GHz) frequencies. Arrays of vertically aligned carbon nanotubes were integrated on a coaxial post in a resonant cavity. In the device simulation shown in Fig. 1a, radiofrequency electromagnetic radiation at the input induces a high, oscillating electric field at the end of the coaxial post; this electric field is further amplified by the carbon-nanotube array (for details, see supplementary information).

The carbon-nanotube array (Fig. 1b) consists of uniform individual carbon nanotubes² spaced at a distance corresponding to roughly twice their height in order to minimize electrostatic-field shielding from adjacent emitters³. Each cathode has an active area of $0.5 \times 0.5 \text{ mm}^2$ (or 2,500 carbon nanotubes) and 16 cathodes can be created simultaneously (Fig. 1b, inset).

The device was operated at 1.5 GHz using various radiofrequency-input powers to generate different macroscopic electric fields at the array of carbon-nanotube emitters. As the cavity walls and emitters are grounded, the radiofrequency electric field exists only inside the cavity, as shown in the equivalent electrical circuit in Fig. 1c. A spectrum analyser connected to the output antenna confirmed the presence of the fundamental 1.5-GHz peak in the cavity. In this study, cathodes were

operated at 1 mA and 1.5 GHz for 40 h without degradation or a decrease in current output (within the measurement error of 5%). With an applied radiofrequency electric field of 29 megavolts per metre, the output at the anode reaches 3.2 mA, with an average current density of 1.3 A cm^{-2} (Fig. 1d). This corresponds to a peak current of 30 mA and a current density of 12 A cm^{-2} in the output waveform (see supplementary information).

The ability directly to generate or modulate an electron beam at high current density and gigahertz frequencies from carbon nanotubes is an important technological advance. Thermionic sources used in today's microwave devices are operated by direct current or at low frequency; their electron beam is usually modulated downstream in an extended interaction line, leading to physically long devices. In contrast, carbon-nanotube cold cathodes that have a vacuum gap to a stand-off grid or anode of a few hundred micrometres or less, as we describe here, have low capacitances and can be operated at very high frequencies (for example, 32-GHz modulation of carbon-nanotube emitters has been achieved from a microwave diode and triode; L.H. et al., manuscript in preparation). They can therefore be used directly as the input stage of a microwave amplifier.

Carbon-nanotube emitters are robust and do not suffer from electromigration because of their strong C–C covalent bonding. Metal emitters, on the other hand, often fail owing to field-induced sharpening, which leads to thermal runaway of the emitters.

Our carbon-nanotube cathode already delivers average- and peak-current densities that are similar to those used in present-day microwave transmission devices. Because of their small size, and ability to generate and modulate the beam directly and on demand without the need for high temperatures, carbon-nanotube cathodes hold promise for a new generation of lightweight, efficient and compact microwave devices for telecommunications in satellites or spacecraft.

Kenneth B. K. Teo*, **Eric Minoux†**,
Ludovic Hudanski‡, **Franck Peauger‡**,
Jean-Philippe Schnell†, **Laurent Gangloff***,
Pierre Legagneux†, **Dominique Dieumegard‡**,
Gehan A. J. Amarasinga*, **William I. Milne***

*Department of Engineering, University of Cambridge, Cambridge CB2 1PZ, UK
e-mail: wim@eng.cam.ac.uk

†Thales Research and Technology, RD 128, 91767 Palaiseau Cedex, France

‡Thales Electron Devices, BP 23, 78141 Vélizy-Villacoublay, France

1. de Jonge, N. & Bonard, J. M. *Phil. Trans. R. Soc. Lond. A* **362**, 2239–2266 (2004).
2. Teo, K. B. K. et al. *Nanotechnology* **14**, 204–211 (2003).
3. Nilsson, L. et al. *Appl. Phys. Lett.* **76**, 2071–2073 (2000).

Supplementary information accompanies this communication on *Nature's* website.

Competing financial interests: declared none.
doi:10.1038/437968a